

Material Safety Data Sheet



1.0 - Product & Company Identification

1.1) Product Name	Supercoat™ Tanking Membrane
1.2) Product Description	Supercoat™ Tanking Membrane is a liquid applied elastomeric waterproofing membrane for use in sealing and waterproofing exposed substrates. Available as Supercoat™ Tanking Membrane and Supercoat™ Tanking Membrane Keycoat, the Keycoat product is used as the final coat where tile adhesive or plaster products are to be applied over. This product is mesh reinforced using a high quality 40 denier 100% polyester mesh at 62gsm with a mesh construction of 62/65. Supercoat™ Deckshield is used as a final coat where a hard wearing, non-slip, trafficable surface is required for general foot traffic. Please refer to the Supercoat™ Deckshield Technical Data Sheet for further information.
1.3) Manufacturer	Ironbark Technology Ltd PO Box 2398 Dunedin New Zealand Phone : +64 3 456 4222 Email : info@ironbark.technology
1.4) Emergency Contact	National Poison Centre 0800 POISON - (0800 764 766) www.poisons.co.nz

2.0 - Hazard Identification

2.1) Grouping Classification	N/A
2.2) Substance Classification	N/A
2.3) UN Number	N/A
2.4) Dangerous Goods Class	N/A
2.5) Hazchem Code	N/A
2.6) HSNO Classification	Non hazardous according to NZ HSNO (Hazardous Substances & New Organisms Act 1996) regulations. Not regulated under NZS 5443:1999 for land transportation.

Material Safety Data Sheet

3.0 - Health Hazard Information

- 3.0) Skin Potentially may cause irritation to skin with prolonged or repeated skin contact.
- 3.1) Eyes Potential to cause irritation to eyes.
- 3.2) Inhalation Repeated and excessive inhalation may result in headaches, nausea, dizziness, asphyxiation.
- 3.3) Swallowed Potentially harmful if swallowed.

4.0 - First Aid

- 4.0) Skin Irritations Remove contaminated clothing and wash thoroughly before re-use. Wash skin thoroughly with water and soap. If skin irritation persists seek medical advice.
- 4.1) Eye Irritations Rinse carefully with water for several minutes. Remove contact lenses if possible and continue to rinse. If irritation persists seek medical advice.
- 4.2) Inhalation Move to a ventilated area with fresh air, rest in a comfortable position for breathing. If respiratory illness persists seek medical advice.
- 4.3) Swallowed If swallowed dilute by drinking 1 or 2 glasses of water, DO NOT induce vomiting. Seek medical advice and/or contact the NZ national poisons centre 0800 POISONS (0800 764 766) immediately.

5.0 - Explosion Hazards

- 5.1) Auto Ignition Temperature N/A
- 5.2) Flash Point N/A

6.0 - Fire Fighting

- 6.1) Extinguishers Use appropriate extinguishers to combat the surrounding fire.
- 6.2) Protective Equipment Self supporting breathing apparatus accompanied by suitably protective clothing.
- 6.3) Hazardous Components Material has boiling point of 100°C, at this point splattering may occur.
- 6.4) Combustion Emissions Carbon Monoxide, Carbon Dioxide and possibly yielding Acrylic Monomer units.

Material Safety Data Sheet

7.0 - Spill Control

- 7.1) Spill Containment Clear the area of surrounding spectators and avoid inhalation of dust and/or vapour emissions. The area will be slippery, take care to avoid falling. Contain spill with an inert material like sand or earthy materials. Remove waste material for disposal. Take care to protect municipal waterways and open bodies of water from any contaminants.
- 7.2) Disposal of Contaminants Incinerate the contaminated material at a permitted facility, or in accordance with all local applicable regulations.

8.0 - Safe Handling & Storage Instructions

- 8.1) Avoiding Contact Avoid contact with eyes, skin and clothing.
- 8.2) Cleaning Clean thoroughly after handling.
- 8.3) Vapours & Emissions Do not breathe vapours or gaseous emissions.
- 8.4) Containment Keep containers closed at all times when not in use.
- 8.5) Storage Store in a well ventilated space.

9.0 - Physical & Chemical Properties

- | | |
|---------------------|---------------------|
| 9.1) Physical State | Liquid |
| pH | 8.7 - 9.3 |
| Specific Gravity | 1.24 - 1.34 |
| Odour | Slightly ammoniacal |
| Boiling Point | 100°C |
| Water Solubility | Completely miscible |